



Triple Pressed and Rubber Grade Stearic acid

Quality Control Data	Pishro Chemical Co.								Sap.value mgKOH/g	Water content %Max	Unsa p %Max	
	Acid Value Mg KOH/g	Iodine Value % Max	Titer °C	LOV Color		%chain distribution						
				R	Y	c14	c12	c16				c18
Triple Pressed Stearic acid	206-213	0.5	55-57	0.2	52-55	0-1	0-2	42-64	58-64	206-214	0.2	1
Rubber Grade Stearic acid	Min196	8.0	Min50	2	min50	0-1	0-2	58-64	42-50	Min196	0.2	1