



## CHLORINATED POLYETHYLENE (CPE)

Characteristic	Result	Test Method
Form	Flake	-
Color	White	-
Viscosity (140°C)/ cP	Max 30.0	ASTM D1986
Softening Point/°C	100 ± 5	ASTM E28
Melting Point /°C	110 ± 5	DSC
Density/ g/cm <sup>3</sup>	0.86±0.03	ASTM D 1505