



Antioxidant 1010

Characteristic	Result
Appearance	White powder or granule
Melting point	110-125°C
Heating loss	≤0.5%
Toluene solubility	Clear
Transmittance 425nm	≥96.0%
Transmittance 500nm	≥98.0%
Ash content	≤0.1%
Effective Content	≥98.0%
Main Content	≥94.0%