



POLYETHYLENE WAX. Code PE 2576

| Characteristic | Result | Test Method |
|-------------------------------|---------------|--------------------|
| Form | Flake | - |
| Color | White | - |
| Viscosity (140°C)/ cSt | 23.34 | ASTM D 1986 |
| Volatile Matter (Moisture)/ % | 8.8 | ASTM D 6658 |
| Needle Penetration/ 0.1mm | 21 | ASTM D 1321 |
| Softening Point/°C | 100 | ASTM E 28 |
| Melting Point /°C | 112 | ASTM D 127 |
| Density/ g/cm ³ | 0.888 | ASTM D 1298 |
| Flash Point/°C | 143 | ASTM D 92 |